

TECHNICAL DATA SHEET



HEXAFOR™ 645

ANIONIC FLUOROSURFACTANT

DESCRIPTION

HEXAFOR[™] 645 is a high performance water soluble anionic fluorosurfactant. It is based on double short-chains containing C6 fluorinated carbon atoms, that cannot breakdown to PFOA in the environment. HEXAFOR™ 645 reduces surface tension at very low concentrations for water based systems.

SPECIAL FEATURES

- Specifically for water-based
- Good reduction of surface tension at very low concentrations
- Excellent leveling
- Improved wetting of aqueous based systems
- Short chain (C6) technology
- Meets the goals of the voluntary U.S. EPA 2010/2015 PFOA Stewardship Program
- ** Targeted below LOD for PFOA (PFOA free*)

TECHNICAL INFORMATION

APPEARANCE	White to pale yellow clear liquid
IONIC NATURE	Anionic
рН	4 - 6
DENSITY	1.13 g/cm ³
MOLECULAR WEIGHT	912
SOLID CONTENT	25-27% (wt)
COMPOSITION	25–27% Active material 23-24% Butyl glycol 49-52% Water

SPECIFICATION

APPLICATION

HEXAFOR™ 645 expresses its best properties already at very low concentration (0.01 - 0.2%).


Some examples of application:

- Paint and varnish
- Waxes and polishes
- Floor strippers, industrial and institutional cleaning
- * Adhesives

SURFACE TENSION IN DEIONIZED WATER AT 25°C

(Wilhelmy plate method.)

- * 15.3 dyn/cm at 0.01 % (active material)
- * 15.0 dyn/cm at 0.05 %
- * 14.9 dyn/cm at 0.1 %
- \div 14.3 dyn/cm at 0.3 %



STORAGE AND STABILITY

HEXAFOR[™] 645 is stable for one year if stored in original closed drums at temperatures of 4 - 45°C (39 - 113°F). Avoid freezing. If frozen let it return to room temperature.

PERSONAL SAFETY

HEXAFOR™ 645 does not contain toxic substances.

VAT N. IT 04080020169 Maflon S.p.A.

REA N. 433424 Cap. Sociale € 100.000 interamente versato

Fluorochemical Specialties



Via Don Ravizza snc 24060 Castelli Calepio (BG) IT Phone +39.035.4494311

http://www.maflon.com - info@maflon.com Accounting Dept. Fax +39.035.4425249 Technical Dept. Fax +39.035.4494331

October 2013. The Information contained in this form and any verbal informations are provided to the best of our knowledge. Not assume responsibility for incorrect or outdated informations, except for agreements reached or otherwise for any contractual obligations. These informations are outdated in the face of publishing a new edition.





TECHNICAL DATA SHEET

Non volatile content: 25 - 27% pH: 4 – 6

SOLUBILITY

Water, 2-propanol, tert-butanol, Hexasol,

* Wherever the term "PFOA Free" is used in this TDS, it means content of PFOA is less than limit of detection (20ppb).

Consult the current Material Safety Data Sheet for safety use of the product.

PACKAGING

- 5Kg Drum
- 25Kg Drum
- 100Kg Drum

Maflon S.p.A. VAT N. IT 04080020169

REA N. 433424 Cap. Sociale E 100.000 interamente versato





UNLEN ISO 9001-2008

Via Don Ravizza snc
 Phone +39.035.4494311
 Fluorochemical Specialties

 Accounting Dept. Fax +39.035.4425249
 http://www.maflon.com - info@maflon.com

October 2013. The Information contained in this form and any verbal informations are provided to the best of our knowledge. Not assume responsibility for incorrect or outdated informations, except for agreements reached or otherwise for any contractual obligations. These informations are outdated in the face of publishing a new edition.